



Kalrez[®] perfluoroelastomer parts

From DuPont Performance Elastomers

Kalrez[®] 4079AMS

Product Description

Kalrez[®] 4079AMS is a specialty black product that meets the requirements of Aerospace Material Specification (AMS) 7257C. It offers outstanding thermal stability, excellent compression set resistance and good seal force retention properties. It also offers excellent resistance to HTS (High Thermo-Oxidative Stability) gas turbine engine lubricating oils and has good response to temperature cycling effects. Kalrez[®] 4079AMS has good mechanical properties and is well suited for both static and dynamic sealing applications. A maximum continuous service temperature of 316°C (600°F) is suggested. Short excursions to higher temperatures may also be possible.

Typical Physical Properties¹

Color	Black
Hardness, Shore A ²	75
100% Modulus ³ , MPa (psi)	7.24(1050)
Tensile Strength at Break ³ , MPa (psi)	16.88 (2450)
Elongation at Break ³ , %	150
Compression Set ⁴ , % 70 hr at 204°C, %	25
Temperature of Refraction, Tr10 ⁵ , °C (°F)	-2 (28)
Maximum Continuous Service Temperature ⁶ , °C (°F)	316 (600)

¹ Not to be used for specification purposes

² ASTM D2240 (pellet test specimens)

³ ASTM D412 (dumbbell test specimens)

⁴ ASTM D395B (pellet test specimens)

⁵ ASTM D1329 (dumbbell test specimens)

⁶ DuPont Performance Elastomers proprietary test method

Performance Features/Benefits

- Outstanding thermal stability
- Excellent compression set resistance
- Excellent resistance to high thermo-oxidative stability (HTS) gas turbine engine lubricating oils
- Good seal force retention properties
- Good response to temperature cycling effects
- Good mechanical strength properties

Comparative Compression Set Resistance¹

Kalrez® 4079AMS exhibits improved resistance to compression set at elevated temperatures versus Competitive FFKM B4.

Test Conditions ²	Kalrez® 4079AMS	Competitive FFKM B4
336 hrs. at 250°C, %	46	82


¹ Not to be used for specification purposes

² ASTM D395B & ASTM D1414 (AS568 K214 O-ring test specimens)

Resistance To Standard And HTS Gas Turbine Engine Lubricating Oils

For many applications, low volume swell of elastomers is critical for proper equipment operation. Excessive swell can lead to material softening, "nibbling", extrusion, etc., causing premature seal failure to occur. While other physical property testing may be needed to adequately define product performance in a particular application, volume swell has historically been used as an indicator of an elastomers' chemical resistance to a particular fluid. Figure 1 shows the long-term volume swell for Kalrez® 4079AMS versus three different types of FKM compounds in both standard and HTS gas turbine engine lubricating oils after 1008 hours at 232°C (450°F). Kalrez® 4079AMS exhibited very low volume swell versus the FKM compounds tested.

Figure 1
Long-Term Volume Swell In Standard* & HTS Gas Turbine Engine Lubricating Oils¹**
 1008 hours at 232°C (450°F) – Oil Changed Weekly²



¹ Not to be used for specification purposes


² ASTM D471 (dumbbell test specimens)

* Air BP Turbo Oil 2380 = standard lubricating oil

** Mobil Jet Oil 254, Mobil Jet Oil 291, Air BP Turbo Oil 2197 & AeroShell™ Turbine Oil 560 = HTS (High Thermo-Oxidative Stability) lubricating oils

Figure 2 shows the long-term compression set properties of Kalrez® 4079AMS versus three different types of FKM compounds in HTS gas turbine engine lubricating oils after 1008 hours with 232°C (450°F). Kalrez® 4079AMS exhibited better resistance to compression set versus the FKM compounds tested.

Figure 2 -- Long-Term Compression Set In HTS* Gas Turbine Engine Lubricating Oils¹
1008 Hours at 232°C (450°F) - Oil Changed Weekly²



¹ Not to be used for specification purposes

² ASTM D395B & D1414 (AS568 K214 O-ring test specimens)

* Mobil Jet Oil 291 & Air BP Turbo Oil 2197 = HTS (High Thermo-Oxidative Stability) lubricating oils

For further information please contact one of the addresses below, or visit us at our website at www.dupontelastomers.com/kalrez

Global Headquarters — Wilmington, DE USA

Tel. +1-800-853-5515
+1-302-792-4000
Fax +1-302-792-4450

European Headquarters — Geneva

Tel. +41-22-717-4000
Fax +41-22-717-4001

South & Central America Headquarters — Brazil

Tel. +55-11-4166-8978
Fax +55-11-4166-8989

Asia Pacific Headquarters — Singapore

Tel. +65-6275-9383
Fax +65-6275-9395

Japan Headquarters — Tokyo

Tel. +81-3-5521-2990
Fax +81-3-5521-2991

The information set forth herein is furnished free of charge and is based on technical data that DuPont Performance Elastomers believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside of our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on any patents. While the information presented here is accurate at the time of publication, specifications can change. Check www.dupontelastomers.com for the most up-to-date information.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont Performance Elastomers customer service representative and read Medical Caution Statement H-69237.

DuPont™ is a trademark of DuPont and its affiliates.

Kalrez® is a registered trademark of DuPont Performance Elastomers.

Mobil™ is a trademark of Mobil.

AeroShell® is a registered trademark of Shell Aviation

Copyright © 2006 DuPont Performance Elastomers. All rights reserved.