



Kalrez® perfluoroelastomer
parts

From DuPont Performance Elastomers

Kalrez® Spectrum™ 0040 For Low Temperature Applications

Kalrez® Spectrum™ 0040 perfluoroelastomer parts are specifically designed for low temperature environments where significant chemical resistance is required. Proprietary polymer and cure technology promotes low temperature sealing performance (-42°C) of Kalrez® Spectrum™ parts to temperatures typically unattainable for perfluoroelastomers parts. Kalrez® Spectrum™ 0040 is an excellent choice in applications such as couplings for the chemical transportation industry, or for other applications, where chemical resistance and elasticity are required in some of the coldest environments. The volume swell for Kalrez® Spectrum™ 0040 is approximately 10% when exposed to nitric acid at 110°C for 168 hours. Compression set resistance is similar to that of our broad chemically-resistant product, Kalrez® Spectrum™ 6375.

Typical Physical Properties¹

Color	Black
Hardness, Durometer Shore A ²	70
100% Modulus ³ , MPa (psi)	6.6 (959)
Tensile Strength at Break ³ , MPa (psi)	13.7 (1885)
Elongation at Break ³ , %	180
Compression Set ⁴ , %	
70 hrs. at 200°C (392°F)	41
336 hrs. at 200°C (392°F)	57
672 hrs. at 200°C (392°F)	62
Upper Service Temperature, °C (°F) ⁵	220 (428)
Lower Service Temperature, °C (°F) ⁵	-42 (-43.6)
Tg °C (°F) ⁵	-27 (-16.6)
Tr10 °C (°F) ⁶	-17(1.4)
<u>Volume Swell (% Change)⁷, 168 hours</u>	
Nitric Acid, 110°C (230°F)	10
Ethylenediamine, 194°F (90°C)	19

¹Not to be used for specification purposes

²ASTM D2240 (pellet test specimens)

³ASTM D412 500mm/min (dumbbell test specimens)

⁴ASTM D395B (AS568 K214 O-ring test specimens)

⁵DuPont Performance Elastomers proprietary test method

⁶ASTM D1329 (slab test specimens)

⁷ASTM D471 (AS568 K214 O-ring test specimens)

For further information please contact one of the offices below, or visit our website at www.dupontelastomers.com/kalrez

Global Headquarters – Wilmington, DE USA

Tel. +1-800-853-5515
+1-302-792-4000
Fax +1-302-792-4450

European Headquarters - Geneva

Tel. +41-22-717-4000
Fax +41-22-717-4001

South & Central America Headquarters - Brazil

Tel. +55-11-4166-8978
Fax +55-11-4166-8989

Asia Pacific Headquarters - Singapore

Tel. +65-6275-9383
Fax +65-6275-9395

Japan Headquarters – Japan

Tel. +81-3-5521-2990
Fax. +81-3-5521-2991

The information set forth herein is furnished free of charge and is based on technical data that DuPont Performance Elastomers believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. While the information presented here is accurate at the time of publication, specifications can change. Check www.dupontelastomers.com for the most up-to-date information.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont Performance Elastomers customer service representative and read Medical Caution Statement H-69237.

DuPont™ is a trademark of DuPont and its affiliates.

Kalrez® Spectrum™ is a registered trademark or trademark of DuPont Performance Elastomers.

Copyright © 2009 DuPont Performance Elastomers. All Rights Reserved.

(12/08) Printed in U.S.A.

Reorder no: KZE-A10769-00-B1109

DuPont
Performance Elastomers

