

Technical Information — Rev. 3, July 2010

Product Description

DuPont™ Kalrez® Spectrum™ 6380 perfluoroelastomers parts are a non-black product specifically developed for chemical processes involving hot, aggressive amines. In addition, it has excellent overall chemical resistance (see chart below). This cream colored product is easily identifiable when selecting an O-ring material for harsh chemical plant services. This material has excellent mechanical properties and is a top choice for both static and dynamic sealing applications. A maximum continuous service temperature of 225 °C is suggested while short-term excursions to higher temperatures are permissible.

For more information on Kalrez® Spectrum™ 6380, or to see if it might be right for your difficult sealing applications in amines and other aggressive chemical streams, please contact DuPont.

Typical Physical Properties¹

Hardness, Shore A ² ±5	80
100% Modulus ³ , MPa (psi)	6.89 (1000)
Tensile Strength at Break ³ , MPa (psi)	15.86 (2300)
Elongation at Break ³ , %	160
Compression Set ⁴ , 70 hr at 204 °C, %	40

¹ Not to be used for specification purposes

² ASTM D2240

³ ASTM D412, 500 mm/min (20 in/min)

⁴ ASTM D395B, size 214 O-ring

Chemical Resistance (672 hour exposure)

Material Compound	DuPont™ Kalrez® Spectrum™ 6380	
<i>Chemical Resistance to:</i>	<i>Temperature, °C</i>	<i>Rating</i>
Acetic Acid	100	A
Nitric Acid (fuming)	60	A
Diethyl Amine	50	A
Monoethanolamine	150	B
Ethylene Diamine	90	A
Butyraldehyde	70	A
Methanol	100	A
Toluene	100	A
Water	225	A

Rating: A: < 10% volume change and minimal effect on elastomer properties
 B: 10–20% volume increase and slight effect on elastomer properties
 C: > 20% volume increase and significant effect on elastomer properties
 X: Elastomer not recommended for this service



The miracles of science™

Visit us at kalrez.dupont.com or vespel.dupont.com

Contact DuPont at the following regional locations:

North America

800-222-8377

Latin America

+0800 17 17 15

Europe, Middle East, Africa

+41 22 717 51 11

Greater China

+86-400-8851-888

ASEAN

+65-6586-3688

Japan

+81-3-5521-8484

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer service representative and read Medical Caution Statement H-50103-3.

Copyright © 2010 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, Kalrez®, Kalrez® Spectrum™, and Vespel® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

(11/06) Reference No. KZE-A10553-00-C0710



The miracles of science™