

Typical Specifications

Comparison of PV, P and V values

Bushing Type	PV	Static P (psi)	Dynamic P (psi)	V (fpm)
FiberLube™ CJ	20,000	60,000	30,000	150
FCJ	20,000	20,000	20,000	500
TH (Dryslide™)	50,000	35,000	20,000	1,000/2,000
Bronze	50,000	8,000	2,000	1,200
Lead Bronze	60,000	3,500	800	1,500
Copper-Iron	35,000	20,000	4,000	225
Iron	30,000	10,000	3,000	400
Bronze-Iron	35,000	10,500	2,500	800
Lead-Iron	50,000	4,000	1,000	800
Aluminum	50,000	4,000	2,000	1,200
Ceramic	40,000	5,000	5,000	∞
Ceramic Liner	30,000	5,000	5,000	400
Polymide/Plastic	9,800	2,300	2,300	360

Essential components for industry

1-800-387-7115

T0G-090